



**DIAMOND
PRODUCERS
ASSOCIATION**



**PROJECT ASSURE
DIAMOND VERIFICATION INSTRUMENT STANDARD REPORT**

**Summary Report for: Dharmanandan Research Centre's (DRC Techno)
/ D-Secure Plus**



Prepared For: Lisa Levinson
Diamond Producers Association Belgium ESV
Hoveniersstraat 22
Antwerp, 2018
Belgium

Received Date: September 25, 2018
Invid Number: 672338
Assessment Dates: May 20, 2019 through May 23, 2019
Testing ID Number: 1908524S-A*
Assessment Testing ID: 1908524
Report Date: August 16, 2019

*This report supersedes the test report dated May 28, 2019. The report was amended to correct the stone color to D-K and the stone size to 0.86mm+(0.003 ct.+).

Approval By:

Judith V Haber

Judith V. Haber
Global Technical Lead Chemistry

LETTERS & REPORTS: UL Verification Services, Inc. (UL) letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the UL name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of UL with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. UL has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.

UL Verification Services, Inc., 85 John Road, Canton, MA 02021
Phone: (781) 821-2200 | Fax: (781) 821-9266 | Website: www.ul.com/consumer-products

	DRC Techno, D-Secure		
	Date:	August 16, 2019	Testing ID:

Manufacturer's Name: DRC Techno
Instrument Model: D-Secure Plus
Serial Number: 20087DP18
Software Version: 1.0.0.4
Lab Manager: Winson Wong
Analyst/Operator: Joseph Tiburcio, Ramesh Pasupleti, Vignesh Kevadiya

Overview

The stated instrument was evaluated to Diamond Verification Instrument Standard Part 1 – Diamond Verification Instrument for Screening Diamonds from Synthetic Diamonds (30 January 2019) as referenced by the Diamond Verification Instrument Standard – General Requirements for Evaluation Diamond Verification Instruments (30 January 2019).

Manufacturer's Claims for Instrument Capability

Sample Composition	
Type of Stones	Diamonds and Synthetic diamonds
Stone Size Range	0.86 mm+ (0.003 ct.+)
Stone Color Range	Stone Color D to K
Loose / Mounted	Loose
Single / Batch Stone Testing	Batch
Automated / Manual Feed	Manual Feed

Summary of Assessment

The instrument has been verified to be able to screen loose, round brilliant cut diamonds and synthetic diamonds in the size range of 0.86 to 3.7 mm (0.003 to 0.2 ct.) and D-J color range.

LETTERS & REPORTS: UL Verification Services, Inc. (UL) letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the UL name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of UL with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. UL has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.

	DRC Techno, D-Secure		
	Date:	August 16, 2019	Testing ID:

Results of Performance Testing to the Diamond Verification Instrument Standard

Test Stone Sets used to Assess Performance

Loose, Polished Stone Test Sets	Diamond	Synthetic Diamond	Diamond Simulant
Primary Set (>2.00 mm, D-J colour) 748 diamonds, 150 synthetic diamonds	☒	☒	☐
Supp. Set A (>2.00 mm, D-J colour) 249 diamonds	☒		
Supp. Set AB (>2.00 mm, D-J colour) 49 synthetic diamonds		☒	☐
Supp. Set B (>2.00 mm, K-Z colour) 250 diamonds	☐		
Supp. Set C (1.00-2.00 mm, D-J colour) 737 diamonds and 140 synthetic diamonds	☒	☒	☐
Supp. Set D (1.00-2.00 mm, D-J colour) 250 diamonds	☒		
Supp. Set DE (1.00-2.00 mm, D-J colour) 51 synthetic diamonds		☒	☐
Supp. Set E (0.10-2.00 mm, K-Z colour) 250 diamonds	☐		

Results of instrument stone assessment testing of Combined Stone Sets - Expert


Test Property	Results for Loose, Polished Stone Test Sets	
	Primary and A&AB Combined	C and D&DE Combined
Diamond accuracy (%)	94.7	96.4
Synthetic diamond accuracy (%)	85.9	96.9
Diamond referral rate (%)	na ^[1]	na ^[1]
Synthetic diamond referral rate (%)	na ^[1]	na ^[1]
Diamond false positive rate (%)	14.1	3.1
Synthetic diamond false positive rate (%)	5.3	3.6
Diamond false negative rate (%)	5.3	3.6
Synthetic diamond false negative rate (%)	14.1	3.1

Notes:

na Not applicable per instrument manufacturer

[1] This instrument does not classify stones as 'Refer'

LETTERS & REPORTS: UL Verification Services, Inc. (UL) letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the UL name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of UL with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. UL has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.

	DRC Techno, D-Secure		
	Date:	August 16, 2019	Testing ID:

Results of instrument stone assessment testing of Combined Stone Sets - Novice

Test Property	Results for Loose, Polished Stone Test Sets	
	Primary and A&AB Combined	C and D&DE Combined
Diamond accuracy (%)	94.7	95.2
Synthetic diamond accuracy (%)	87.4	96.3
Diamond referral rate (%)	na ^[1]	na ^[1]
Synthetic diamond referral rate (%)	na ^[1]	na ^[1]
Diamond false positive rate (%)	12.6	3.7
Synthetic diamond false positive rate (%)	5.3	4.8
Diamond false negative rate (%)	5.3	4.8
Synthetic diamond false negative rate (%)	12.6	3.7

Notes:

na Not applicable per instrument manufacturer

[1] This instrument does not classify stones as 'Refer'


Results of instrument testing speed assessment - Expert

Rate of Testing Speed Test Method	Average Test Result
<input type="checkbox"/> Test Method A: Fixed number of stones	948 stones per hour
<input checked="" type="checkbox"/> Test Method B: Fixed time frame	
<input type="checkbox"/> Test Method C: Reduced number of stones	

Results of instrument testing speed assessment - Novice

Rate of Testing Speed Test Method	Average Test Result
<input type="checkbox"/> Test Method A: Fixed number of stones	600 stones per hour
<input checked="" type="checkbox"/> Test Method B: Fixed time frame	
<input type="checkbox"/> Test Method C: Reduced number of stones	

LETTERS & REPORTS: UL Verification Services, Inc. (UL) letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the UL name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of UL with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. UL has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.

	DRC Techno, D-Secure				
	Date:	August 16, 2019	Testing ID:	1908524S-A	

Results of instrument stone assessment testing of individual stone sets - Expert

Test Property	Results for Loose, Polished Stone Test Sets					
	Primary	A & AB	B & AB	C	D & DE	E & DE
Diamond accuracy (%)	94.4	95.6	na	96.1	97.2	na
Synthetic diamond accuracy (%)	85.3	87.8	na	97.9	94.1	na
Diamond referral rate (%)	na ^[1]	na ^[1]	na	na ^[1]	na ^[1]	na
Synthetic diamond referral rate (%)	na ^[1]	na ^[1]	na	na ^[1]	na ^[1]	na
Diamond false positive rate (%)	14.7	12.2	na	2.1	5.9	na
Synthetic diamond false positive rate (%)	5.6	4.4	na	3.9	2.8	na
Diamond false negative rate (%)	5.6	4.4	na	3.9	2.8	na
Synthetic diamond false negative rate (%)	14.7	12.2	na	2.1	5.9	na

Notes:

na Not applicable per instrument manufacturer

[1] This instrument does not classify stones as 'Refer'

Results of instrument stone assessment testing of individual stone sets - Novice

Test Property	Results for Loose, Polished Stone Test Sets					
	Primary	A & AB	B & AB	C	D & DE	E & DE
Diamond accuracy (%)	97.1	87.6	na	95.4	94.8	na
Synthetic diamond accuracy (%)	88.7	83.7	na	97.1	94.1	na
Diamond referral rate (%)	na ^[1]	na ^[1]	na	na ^[1]	na ^[1]	na
Synthetic diamond referral rate (%)	na ^[1]	na ^[1]	na	na ^[1]	na ^[1]	na
Diamond false positive rate (%)	11.3	16.3	na	2.9	5.9	na
Synthetic diamond false positive rate (%)	2.9	12.4	na	4.6	5.2	na
Diamond false negative rate (%)	2.9	12.4	na	4.6	5.2	na
Synthetic diamond false negative rate (%)	11.3	16.3	na	2.9	5.9	na

Notes:

na Not applicable per instrument manufacturer

[1] This instrument does not classify stones as 'Refer'

Additional Notes from Assessment Findings

Below is a summary of an additional findings from assessment:

- No additional comments

LETTERS & REPORTS: UL Verification Services, Inc. (UL) letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the UL name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of UL with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. UL has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.

	DRC Techno, D-Secure		
	Date:	August 16, 2019	Testing ID:

Definitions

Diamond Accuracy	Defined as the fraction of test stones correctly classified by the specific diamond verification instrument as diamond.
Synthetic Diamond Accuracy	Defined as the fraction of test stones correctly classified by the specific diamond verification instrument as synthetic diamond.
Diamond Referral Rate	Defined as the fraction of diamonds that could not be classified by the specific diamond verification instrument and requires further.
Synthetic Diamond Referral Rate	Defined as the fraction of synthetic diamonds that could not be classified by the specific diamond verification instrument and requires further testing.
Diamond False Positive Rate	Defined as the fraction of synthetic diamonds and/or diamond simulants incorrectly classified as diamond by the specific diamond verification instrument.
Synthetic Diamond False Positive Rate	Defined as the fraction of diamonds and/or diamond simulants incorrectly classified as synthetic diamonds by the specific diamond verification instrument.
Diamond False Negative Rate	Defined as the fraction of diamonds incorrectly classified as synthetic diamond and/or diamond simulant by the specific diamond verification instrument.
Synthetic Diamond False Negative Rate	Defined as the fraction of synthetic diamonds incorrectly classified as diamond and/or diamond simulant by the specific diamond verification instrument.
Rate of Testing Speed	Defined as the average speed at which the diamond verification instrument evaluates unknown stones.

***** End of Report *****

LETTERS & REPORTS: UL Verification Services, Inc. (UL) letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the UL name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of UL with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. UL has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.